

Sample Number: **Z36343**
Page 1 of 1

Client: Macismo International Ltd **Lab. Scheme Number:** 9848
Product for test: MACFIX TREATED BINDER
Date sampled: n/a
Date Received: 06/06/2007
Date Tested: 11/06/2007

Test Procedure:

Distillation of Cut-Back Bitumen - ASTM D 402 - 87

Test Results:

Distilate to 225° C (volume %): **0**
Distilate to 260° C (volume %): **0.8**
Distilate to 316° C (volume %): **2.8**

Total Distilate (TD) to 360° C (volume %): **10.8**

Note: This is an amended copy of certificate no Z36343

Distribution

Macismo International Ltd
13 Cover Green
Worcester
WR4 0JF

Authorised By: _____

Approved Signatories
I.G.L.Valentine
D.J.Green
P.G.Shrubsole

f.a.o. Doug Shipsey

Date: 23-Jul-07